

Description

Polyisocyanurate rigid foam

Blowing agents:

CFCs/HCFCs-free

Approvals, Homologations, Compliances

ASTM C 591–Type IV–Grade 2

Characteristics

| | | | |
|--|-------------------------------|--|-----------------------|
| Color | | | Green |
| Nominal density | ASTM D1622/EN 1602/EN ISO 845 | lb/ft ³ (kg/m ³) | 2 (32) |
| Compressive resistance – Parallel (74°F/23°C) | ASTM D1621/EN 826 | psi (MPa) | 32 (0.220) |
| Compressive resistance - Perpendicular (74°F/23°C) | ASTM D1621/EN 826 | psi (MPa) | 22 (0.151) |
| Tensile strength - Parallel (74°F/23°C) | ASTM D1623-A/EN 1607 | psi (MPa) | 50 (0.345) |
| Tensile strength - Perpendicular (74°F/23°C) | ASTM D1623-A/EN 1607 | psi (MPa) | 36 (0.250) |
| Shear strength - Perpendicular (74°F/23°C) | ASTM C273/EN 12090 | psi (MPa) | 23 (0.160) |
| Thermal conductivity - Initial (75°F/24°C) | ASTM C518/EN 12667 | BTU-in/hr-ft ² ·°F (mW/mK) | 0.160 (22.9) |
| Thermal conductivity - 180 days (75°F/24°C) | ASTM C518/EN 12667 | BTU-in/hr-ft ² ·°F (mW/mK) | 0.183 (26.0) |
| Surface burning characteristics | ASTM E84 | FSI | <25 |
| Surface burning characteristics | ASTM E84 | Smoke Dev. | <450 |
| Horizontal burning characteristics | UL 94/ASTM D4986 | | HF-1 |
| Dimensional stability (-40°F/-40°C, 7 days) - linear change (length) | ASTM D2126/EN 1604 | % | 0.5 |
| Dimensional stability (+212°F/+100°C, 7 days) - Linear change (length) | ASTM D2126/EN 1604 | % | 1.0 |
| Dimensional stability (+158°F/70°C, 97% R.H., 7 days) - Linear change (length) | ASTM D2126/EN 1604 | % | 2.5 |
| Water vapor permeability (74°F/23°C,50% R.H.) | ASTM E96/EN 12086 | Perm-inch (ng/s·m·Pa) | <4 (5.8) |
| Water absorption by volume | ASTM C272 | % | <0.6 |
| Operating temperature | | °F (°C) | -320/+300 (-196/+149) |
| R-Value - 180 days, 1 inch (75°F/24°C) | ASTM C518/EN 12667 | hr-ft ² ·°F/BTU (m ² ·K/W) | 5.46 (0.97) |
| Closed-cell content | ASTM D6226/EN ISO 4590 | % | >92 |
| Hot-Surface Performance (300°F/149°C) | ASTM C411 | | Pass |

Handling notice

Terms "parallel" and "perpendicular" are referred to slab/specimen/block thickness direction.

Above 300°F, discoloration and surface carbonization will occur, involving possible changes of the physical and mechanical properties of the material.

DUNA-USA INC. - Headquarters: 4210 FM 1405 - Baytown, TX 77523 - Ph: 281-383-3862 - Fax: 281-383-0115

Michigan plant: 5900 West 6th street, Ludington, MI 49431

Web: www.dunagroup.com/usa/home - Email: info-dunausa@dunagroup.com



In some applications polyurethane may present fire risks, e.g. if exposed to fire or to excessive heat in presence of oxygen or air, including when welding or cutting with torches.

It is the Customer's responsibility to determine if product described herein is appropriate for Customer's purposes and end-use and to ensure that working place, storage and disposal practices are in compliance with any applicable law.

Remarks

For usage information, personal protective equipment, transport, storage and disposal of waste it is essential to refer to the Material Safety Data Sheets.

Values shown are determined from laboratory tests and obtained under controlled conditions; they outline typical characteristics and they do not constitute anyhow a sales specification; they are based on DUNA-USA's current knowledge and experience of the products when properly stored, handled and applied in accordance with our recommendations.

This Technical Data Sheet cancels and replaces any other previous issue.

DUNA-USA does not accept responsibility for incorrect use of its products as it cannot ensure the correct methods of application have been followed; we therefore specifically disclaim any liability for consequential or incidental damages of any kind, including lost profits.

DUNA-USA reserves the right to change the data in this information sheet without any prior notice.
